

ERIC PELLE


MADERA

Bolivia finest exotic wood compamy



MORADO

Palisander Santos



Name: MORADO (*Machaerium scleroxylon*)

Other names: Bolivian Rosewood, Santos Palisander, aviuna, Pau-ferro, Jacarandá-violeta

Family: Dalbergieae

Janka Hardness: 2,139 pounds

Strength (MOR): 17,750 psi

Stiffness (MOE): 1,574 1000 psi

Density (KG/m³): 880

Radial Shrinkage: 2.8 %

Tree Characteristics: The Morado trees grows up to 100 feet tall with a diameter of up to 5 feet.

Color: Heart and sapwood can be highly varied, ranging from reddish/orange to a dark violet/-brown, usually with darker black streaks.

Texture: Fine to coarse.

Grain: Straight to irregular..

Luster: Medium to high.

Durability Rating: Highly resistant to decay and fungi.

Applications: Flooring, decorative veneers, specialty items, cabinet work.