

# ERIC PELLE

## MADERA

*Bolivia finest exotic wood compamy*



### TARARA AMARILLA

Canary wood



Name: CANARYWOOD (*Centrolobium microchaete*)

Other names: Tarara Yellow, Canary.

Janka Hardness: 2,410 pounds

Strength (MOR): 18,000 psi

Stiffness (MOE): 2,130 1000 psi

Density (KG/m<sup>3</sup>): 740

Tangential Shrinkage: 4.0 %

Radial Shrinkage: 3.0 %

Tree Characteristics: The Canarywood tree can grow up to 100 feet high.

Color: Bright yellow to orange heartwood with streaks of dark purple/black.

Texture: Medium and uniform.

Grain: Irregular and interlocked.

Luster: Medium to high.

Durability Rating: Good durability rating.

Drying Characteristics: Moderate.

**Applications: Flooring, cabinet work, furniture, joinery, turnery, decorative veneers.**