

ERIC PELLE

MADERA

Bolivia finest exotic wood compamy



Curupau

Curupay



Name: CURUPAY (Anadenanthera colubrina)

Other names: Curupay, Curupau, Angico Preto.

Janka Hardness: 3,630 pounds

Strength (MOR): 28,010 psi

Stiffness (MOE): 2,617 1000 psi

Density (KG/m3): 1,030

Tangential Shrinkage: 7.6 %

Radial Shrinkage: 4.6 %

Tree Characteristics: The Curupay tree can reach a height of 80 feet.

Color: Reddish-brown heartwood with near-black streaks, yellow-brown to light pink sapwood.

Texture: Fine and uniform.

Grain: Irregular and interlocked.

Durability Rating: Rated as very durable.

Working Characteristics: Rated as difficult to work, causing blunting on cutting edges.

Applications: Flooring, railroad cross ties, tool handles, heavy exterior construction.