

ERIC PELLE

MADERA

Bolivia finest exotic wood compamy



GUAYACAN

Brown Ebony



Name: BROWN EBONY
(*Caesalpinia paraguariensis*)
Other names: GUAYACAN

Janka Hardness: 3,590 pounds
Strength (MOR): 22,910 psi
Stiffness (MOE): 2,712 1000 psi
Density (KG/m3): 1,025
Tangential Shrinkage: 7.7%
Radial Shrinkage: 4.5%

Tree Characteristics: 30-50 ft (10-15 m) tall, 2-3 ft (.6-1.0 m) trunk diameter
Color: Heartwood is a dark brown, sometimes with a reddish hue. Pale yellow sapwood is clearly

Texture: Uniform medium to coarse
Grain: Straight to irregular or interlocked.
Luster: Moderate natural luster

Durability Rating: Rated as very durable, though susceptible to insect attack.

Applications: Veneers, musical instruments, turnery, industrial flooring, decking, furniture, doors