

ERIC PELLE


MADERA

Bolivia finest exotic wood compamy



Tarara Colorada

Tarara Red



Name: PARA ROSEWOOD (Platymiscium spp.)

Other names: Macacauba, Macawood, Tarara Red.

Janka Hardness: 2,450 pounds

Strength (MOR): 27,600 psi

Stiffness (MOE): 3,200 1000 psi

Density (KG/m3): 880

Tangential Shrinkage: 3.5 %

Radial Shrinkage: 2.7 %

Tree Characteristics: Para Rosewood tree can grow up to 80 feet tall.

Color: Para Rosewood 's heartwood tends to be red to purplish-brown, with distinct striping.

Texture: Mostly medium, fine, sometimes coarse.

Grain: Straight to roey.

Luster: Medium to high.

Durability Rating: Rated highly resistant to decay fungi and insects.

Drying Characteristics: Air dries slowly with slight tendencies towards warping and checking.

Applications: Furniture, cabinet work, decorative veneer, musical instruments, joinery, turnery, flooring